

Webster: Baber Colman 換算表

Rockwell			Brinell	Webster	Baber Colman	Rockwell
HRB	HRE	HRF	HB	刻劃		HRE
100				4	54	41
99			238	5	56	45
98			234	6	57	49
97			225	7	59	54
96			216	8	62	58
95			210	9	63	62
94			205	10	67	67
93			200	11	68	71
92			195	12	71	75
91			190	13	73	49
90		107.5	185	14	75	83
89			180	15	79	88
88			176	16	82	92
87			172	17	85	96
86		106	169	18	90	101
85		105.5	165			
84		105	162			
83		104.5	159			
82		104	156			
81			153			
80			150			
79		102.5	146			
78		102	144			
77		101	141			
76		100.5	139			
75		100	137			
74			135			
73		98.5	132			
72		98	130			
71	100	97.5	127			
70	99.5	97	125			
69	99	96.5	123			
68	98	96	121			
67	97.5	95.5	119			
66	97	95	117			
65	96	94.5	116			
64	95.5	94	112			
63	95	93	110			
62	94.5	92.5	108			
61	93.5	92	107			
59	92		104			
58		90.5	103			
57	91	8.8	101			
56	90	89	100			
54	89	88	95			
52	88	87.2	94			
51	87	86.2	92			
49	86	85	89			
47	85		86			
46	84	83	84			
44	83		81			
43	82	81	80			
41	81	80				
39	80					
38	79	78				
36	78	77				
34	77	76				
33	76	75				
31	75	74				
2	74	73				
28	73					
26	72					
24	71	70				
23	70					
21	69					
20		68				
19	68					
18		67				
17	67	66				
16	66					
15		65				
14	65					
13	64	64				
11	63	63				
9	62	62				
8	61	61				
6	60	60				
4	59	59				
2	58	58				
1	57	57				
	56	56				
	54	54				
	52	52				
	51	51				
	50	50				
	48	49				
	46	47				
	44	46				
	42	44				
	40	42				
	38	40				
	36	38				

3/8inch 測頭 測試材料厚度最大1/4inch
 Model B 測試1100-2014系列鋁合金
 硬度範圍Hre25-Hre110
 標準試片 鋁合金6061-T6
 標準試片標準值Hre90-92/請值16.5刻劃